



# Singlemode (Stufenindexfaser)

## Monomode (step index fibre)

### Anwendung

Singlemodefasern finden hauptsächlich in Weitverkehrssystemen mit großen Informationsmengen und Regeneratorabständen Anwendung. Diese Fasertyp ist weltweit in privaten und öffentlichen Telekommunikationsnetzen im Einsatz. Diese Fasern bestehen aus einem hochreinen Quarzglaskern umgeben von einem Quarzglasmantel. Die Faser wird von einer UV-gehärteten Acrylat-Schicht geschützt. Diese Fasern erlauben, zufolge ihrer niedrigen Dämpfungs- und Dispersionswerte, den Einsatz auch in Weitverkehrssystemen.


### Aufbau



### Application

Single-mode fibres are primarily used for long-distance systems where volumes of data are transmitted across wide distances between regenerators. The fibre is used in numerous private and public telecommunication networks all over the world. The fibre consists of a highly pure silica core, surrounded by silica cladding. The fibre is protected by a layer of Uv-harden acrylate owing to their low attenuation and dispersion values, the „matched cladding“-type fibre may also be used in longterm solutions that offer a secure basis for future developments.

### Construction



### Technische Daten

### Technical Data

|  |                       | ITU-T G.652D  | ITU-T G.657.A1 | TU-T G.657.A2 | TU-T G.657.B3 | TU-T G.655.C/D | TU-T G.655.C/E G.656 |
|--|-----------------------|---------------|----------------|---------------|---------------|----------------|----------------------|
| Dämpfung /attenuation<br>@ 1310 nm (typ. / max.)                   | dB/km                 | 0,31 / 0,35   | 0,31 / 0,35    | 0,31 / 0,35   | 0,31 / 0,35   | -              | -                    |
| @ 1550 nm (typ. / max.)  | dB/km                 | 0,20 / 0,24   | 0,20 / 0,24    | 0,20 / 0,24   | 0,20 / 0,24   | 0,25 / 0,30    | 0,25 / 0,30          |
| @ 1625 nm (typ. / max.)  | dB/km                 | 0,21 / 0,26   | 0,21 / 0,26    | 0,21 / 0,26   | 0,21 / 0,26   | 0,27 / 0,34    | 0,27 / 0,34          |
| Chromatische Dispersion / chromatic dispersion<br>@ 1285-1330 nm   | ps nm.km              | ≤ 3,5<br>≤ 18 | -              | -             | -             | -              | -                    |
| @ 1550 nm  | -----                 | -             | -              | -             | -             | -              | -                    |
| @ 1530-1565 nm   | nm.km                 | -             | -              | -             | -             | 2,6 - 6,0      | 5,5 - 8,9            |
| @ 1565-1625 nm   | -----                 | -             | -              | -             | -             | 4,0 - 8,9      | 6,9 - 11,4           |
| @ 1460-1625 nm   | -----                 | -             | -              | -             | -             | -1,0 - 8,9     | 2,0 - 11,4           |
| Nulldispersionswellenlänge ( $\lambda_0$ ) / zero disp. wavelength | nm                    | 1302-1322     | 1302-1322      | 1302-1322     | 1302-1324     | -              | ≤ 1405               |
| Grenzwellenlänge ( $\lambda_{cc}$ ) / cut-off wavelength           | nm                    |               |                | ≤ 1260        |               | -              | -                    |
| Faser PMD / fibre PMD individual fiber                             | ps $\sqrt{\text{km}}$ |               | 0,1            |               | 0,2           |                | 0,1                  |
| Durchmesser des Modenfeldes / mode-field diameter<br>@ 1310 nm     | μm                    | 9,2 ± 0,4     | 8,6 - 9,3      | 8,8 ± 0,4     | 6,3 - 9,5     | -              | -                    |
| @ 1550 nm  | μm                    | 10,4 ± 0,5    | 9,5 - 10,5     | -             | 9,2 - 10,4    | 8,4 ± 0,6      | 8,6 ± 0,4            |
| Manteldurchmesser / cladding diameter                              | μm                    |               |                |               | 125 ± 0,7     |                |                      |
| Mantel Unrundheit / clad non-circularity                           |                       |               | ≤ 1%           |               | ≤ 1 μm        |                | ≤ 0,7%               |
| Durchmesser Primärbeschichtung / coating diameter                  | μm                    |               | 235 - 245      |               | 245 ± 10      |                | 245 ± 5              |
| Primär-/Mantel Exzentrizität / coating/clad concentricity          |                       |               | ≤ 12 μm        |               | ≤ 5%          |                | ≤ 10 μm              |
| Kern/Mantel Exzentrizität / core/clad concentricity                | μm                    |               | ≤ 0,5          | -             |               | ≤ 0,5          |                      |
| Brechungsindex / refractive index<br>@ 1310 nm                     |                       |               | 1.467          | -             | -             | 1.471          |                      |
| @ 1550 nm  |                       |               | 1.468          | -             | 1.468         |                | 1.470                |